

ONE-PART POLYURETHANE LOW MODULUS CONSTRUCTION SEALANT

DESCRIPTION

U-Seal 907 is a one-component, gun-grade, non-sag polyurethane construction sealant. It cures under the influence of atmospheric moisture to form a high-performance compound with permanent elasticity and resistance to ageing and weathering.

RECOMMENDED FOR

- ▶ Sealing expansion and construction joints in vertical and horizontal applications
- ▶ Joints in precast elements
- ▶ External walling and cladding joints
- ▶ Weatherproofing of joints between brickwork, block-work, masonry, wood, concrete, metal frames
- ▶ Joints in walls, floors, balconies, around window or door frames
- ▶ Joints in water channels and suitable for hydraulic general sealing with contact with water
- ▶ Bridge and balcony parapets
- ▶ Retaining walls
- ▶ Metal roof and gutter sealing

ADVANTAGES

- ▶ Bonds and seals at the same time
- ▶ Permanently elastic; accommodates joint movement of $\pm 50\%$
- ▶ Easy to gun with excellent tooling consistency
- ▶ Performant adhesion on all typical construction and industrial materials
- ▶ Good thixotropy - Non-sagging
- ▶ Non-staining on concrete and porous materials
- ▶ Excellent primerless adhesion on all typical construction and industrial materials
- ▶ Good resistance to ageing, weathering and immersion in cleansing agents, sea water, lime water
- ▶ Over-paintable with many water and solvent based paints (preliminary tests recommended)

TECHNICAL CHARACTERISTICS

Characteristics	Test Result	Test Method
Appearance	Non-sag thixotropic paste	
Chemical nature	Polyurethane	
Color	Grey, white, black. Other on request	
Curing mechanism	Moisture-curing	
Curing through volume	ca. 2 mm	At 23 °C (73,4 °F) and RH 50%
Shore A hardness	ca. 30	DIN 53505
Density	ca. 1,34 g/cm ³ (83,65 lb/ft ³)	At 23 °C (73,4 °F) and RH 50%
Tack-free time	ca. 120 min	At 23 °C (73,4 °F) and RH 50%
Elastic modulus at 100%	ca. 0,4 N/mm ²	ISO 37 DIN 53504
Tensile strength	ca. 1,5 N/mm ²	ISO 37 DIN 53504
Elongation	ca. 750%	ISO 37 DIN 53504
Joint Movement Capability	$\pm 50\%$ of joint width	ASTM C920
Application temperature	5 to 40 °C (41 to 104 °F)	
Temperature resistance	-40 to 100 °C (-40 to 212 °F) with brief points at 120 (248 °F)	

Note: All data are average values obtained under laboratory conditions. Impractical use, temperature, humidity and absorption of the substrate may influence the above given values.



ONE-PART POLYURETHANE LOW MODULUS CONSTRUCTION SEALANT

DIRECTIONS FOR USE

Surface Preparation: Surfaces must be clean, dry, free of water, oil, grease or rust and of sound quality. Remove all loose particles or residues with a jet of compressed air, sandpaper or hard brush. Glass, metal and other non-porous surfaces must be free of any coatings and wiped clean with solvent. Pre-cast panels using form-release agents other than polyethylene film must be sandblasted or mechanically abraded and dust free. U-SEAL 907 has very good adhesion properties without the use of primer on most common building materials. Consequently, the use of the primer is not necessary if the support to be sealed is properly prepared and consolidated. However, varieties of brick, natural stone, plastics, paints, coatings and other treatments of surfaces often presents a difficult surface to which to adhere. Due to the number of unpredictable natures of these substrates, a preliminary test is recommended. If necessary, apply a coating of primer on the joint walls (U-Primer 110 for porous surfaces).

For sealing purposes: Recommended application temperatures: 15°-25°C (59 – 77 °F). For easier use or cold weather application we recommend the material to be stored at approximately 25°C (77 °F) prior to use. In order to guarantee free movement of the sealant in joints, it is imperative that the sealant does not adhere to the bottom of the joint, therefore for correct joint caulking, a closed-cell polyethylene bead (joint backing rod) PENETRON® BACKING ROD of suitable diameter is to be placed at the proper depth. If necessary, apply appropriate primer to joint sides and observe waiting time to avoid that trapped solvent, in condition of rising temperature, can blow bubbles in the uncured sealant. For best performance, sealant should be gunned into joint when the joint slot is at mid-point of its designed expansion and contraction. Firmly extrude sealant into the joint making sure that it is in full contact with the sides of the joint and with the backing rod at the bottom. Keep the nozzle in the sealant, continue on with a steady flow of sealant preceding the nozzle to avoid air entrapment. Avoid overlapping of sealant to eliminate entrapment of air.

Finishing indications and limitations: Sealant should be tooled to a smooth finish ensuring a full contact to the sides and back up material into the joint, this will also contribute in breaking the air bubbles which may be formed inside the sealant. Masking tape should be used where sharp exact joint lines or exceptionally neat lines are required. Remove the tape whilst the sealant is still soft.

Coverage 6 linear meters of 1 x 1 cm joint per 600 mL cartridge.

SPECIAL CONSIDERATIONS

U-Seal 907 may be painted. However, some coatings may crack if movement occurs, preliminary tests recommended. Avoid exposure to high levels of chlorine (avoid to seal joints in chlorinated swimming pools). Do not cure in the presence of curing silicone sealants. Avoid contact with alcohol and other solvent cleaners during cure.

Do not apply when moisture or vapour transmission condition exists from the substrate as this can cause bubbling within the sealant. White colour tends to yellow slightly when exposed to ultraviolet rays. The ultimate

performance of U-Seal 907 depends on good joint design and proper application with joint surfaces properly prepared.

Clean the tools used with acetone or solvent.

Cured material can only be removed mechanically.

Contact PENETRON HELLAS S.A. for further information, regarding your project.

PACKAGING

U-SEAL 907 can be purchased in unipacks of 600 mL (37 in³) (20 pieces per box).

STORAGE / SHELF LIFE

U-Seal 907 can be stored for 12 months in its original packaging (unopened container) at 10°C - 25°C (50 °F - 77 °F) in a cool, dry place. The storage temperature should not exceed 25°C (77 °F) for extended periods of time. Keep away from wet areas, direct sunlight and heat sources.

SAFE HANDLING INFORMATION

Avoid skin and eye contact. If in eye, flush immediately with lots of water and seek medical advice. If skin contact occurs, remove immediately and wash with soap and water. KEEP OUT OF REACH OF CHILDREN. For further information please refer to Safety Data Sheet. PENETRON HELLAS S.A. has recently updated Safety Data Sheet on the safe use of PENETRON® products. Each Safety Data Sheet contains health and safety information for the protection of your employees and your customers.

CERTIFICATION

Certified according to:

EN 15651-1/4 TYPE F INT/EXT CC/ PW INT/EXT CC
ASTM C920 Type S Grade NS Class 50 Use T2, M, A, O, L.

Compliant to:

ISO 11600 Type F Class 25 sub-class LM;
LEED iEQc 4.1; SCAQMD Rule 1168; BAAQMD Reg 8
Rule 51



2538
EN 15651-1
EN 15651-4
NPT srl

Via G.Rossa 2
Loc. Crespellano – 40053 Valsamoggia (BO)
Italy
14
U-SEAL 907

One component polyurethane
for the application in facade and pedestrian walkways
Type F EXT-INT CC / PW EXT-INT CC
Conditioning: Method A
Substrate: Mortar M1
Pre – treatment with U-Primer 110 (mortar)

ONE-PART POLYURETHANE LOW MODULUS CONSTRUCTION SEALANT

Reaction to fire: Class E

Release of chemicals dangerous to the environment and health:
NPD

Water tightness and air tightness

- a) Resistance to flow: ≤ 3 mm
- b) Loss of volume: ≤ 10 %
- c) Tensile properties at maintained extension after water immersion: Not failure
- d) Tensile properties at maintained extension: Not failure
- e) Tensile properties at maintained extension at -30°C : Not failure
- f) Tensile properties (secant modulus) at 23°C : ≤ 0.4 N/mm²
- g) Tensile properties (secant modulus) at -20°C : ≤ 0.6 N/mm²
- h) Tensile properties (secant modulus) at -30°C : ≤ 0.9 N/mm²
- i) Adhesion/cohesion properties at maintained extension after 28days water immersion: Not failure
- j) Adhesion/cohesion properties at maintained extension after 28days salt water immersion: Not failure
- k) Tear resistance: Not failure
- l) Durability: Pass

WARRANTY - DISCLAIMER

PENETRON HELLAS S.A. warrants that its products are manufactured under certified ISO Standard procedures, are of excellent quality and shall be free from material defects and contain all components in their proper proportion. Should any of the products be proven defective, the liability to PENETRON HELLAS S.A. shall be limited to replacement of the material proven to be defective, since the standard application procedures have been met and the suitability of the product for the particular application have been proven. PENETRON HELLAS S.A. makes no warranty as to merchantability of fitness for a particular purpose. User, after contacting the distributor of the product, shall determine the suitability of the product for his intended use and assume all risks and liability in connection therewith. While every care has been taken, the information provided in this product's data sheet make no part of any contract. All recommendations, technical data and test data contained in this product's data sheet are based upon the results of control laboratory tests or in actual field tests. However, PENETRON HELLAS S.A. makes no warranty of any kind, concerning this data. In any case, this data is given in good faith based in the PENETRON HELLAS S.A. experience, till the publication of this sheet. Due to variance in storage, handling and applications of the materials, PENETRON HELLAS S.A. accepts no liability for the results obtained. It is suggested that potential users try small applications to determine the suitability of each individual product for their specific requirements. The users should always refer to the most recent edition of the product's data sheet. PENETRON HELLAS S.A. may particularly differentiate its versions of the product's data sheet compared with those of PENETRON INTERNATIONAL LTD or respective PENETRON companies worldwide. These changes are due to text formatting, different application weathering and procedures or different product names and aim at the optimal consumer information.

CONCRETE PROTECTION SYSTEM
House/Flat # 5A, Plot # Ta-94/B,
Road # Boishakhi Saroni, Middle Badda -
Dhaka-1212 info@cpswaterproofing.com
cpswaterproofing.com 01613-239093

PENETRON HELLAS S.A.
G.E.MH. No: 07278001000
Athens Headquarters - Greece
50 - 52, Thrakomakedonon Av.
136 79 Acharnes, Greece
T: +30 210 2448250
F: +30 210 2476803
info@penetron.gr, www.penetron.gr